

Survey „thermal - oil“

Producer	Type	max. Pre-run-temperature °C	cracking temperature °C
SINGLE	„S“	350	370
BP	Olex WF 0801	350	370
CHEM.WERKE HÜLS	Marlotherm SH	350	370
HOUGHTON	Transtherm 617	350	370
ARAL	Farolin U	320	350
MOBIL	Mobiltherm 603	285	315
Fragol	Therminol 66	355	375
DURATHERM EXTENDED LIFE FLUIDS	Duratherm FG	330	350
SINGLE	„M“	320	340
BP	Transcal 65	320	340
ESSO	Thermaöl T	320	340
FINA	Caloran 32	320	340
TEXACO	Texatherm HT	320	340
SHELL	Thermia B	310	340
FRAGOL	Therminol 59	310	340
ARAL	Farolin S	300	330
ESSO	Thermaöl T	300	320
ARAL	Farolin T	270	300
FRAGOL	Ucotherm S-20-A	220	250
HOUGHTON	Transtherm 7	200	250
PETRO-CANADA/FRAGOL	Calflo AF	300	345
PETRO-CANADA/FRAGOL	Calflo FG	325	345
SHELL	Cassida Fluid HT 32	280	320
SHELL	FM Heat Transfer Fluid 32	325	340
DURATHERM EXTENDED LIFE FLUIDS	Duratherm 450	230	250

By using different types of oil, please set film temperature limiting switch on cracking temperature!.